

M723A CHOPPED STRAND MAT

FOR DEMANDING APPLICATIONS



DESCRIPTION

M723A is a fine fiber and medium bundle Tex chopped strand mat that produces a good surface finish while still maintaining fast wetting properties. It is multi-chop length construction results in improved conformability while still maintaining exceptional mechanical properties. The M723A chemistry is multi-resin compatible.

BENEFITS

- **Quick wetting and rapid air release:** Maximizes molding productivity by reducing the labour required to roll out product.
- **Excellent weight uniformity:** Translates to more consistent customer product uniformity.
- **Exceptional wet tensile strength:** Well suited for pre-wetting ("wet and carry") applications.
- **Superior glass bonding:** Excellent dry handling characteristics and minimal fiber shedding.
- **Externally Certified:** Lloyd's Register of Shipping and Det Norsk Veritas.
- **Superior corrosion resistance with Advantex® Glass compared to standard E-glass:** Advantex® Glass helps with enhanced life and service life strength in applications facing corrosion. For additional information on Advantex® glass use the link below: <http://composites.owenscorning.com/aboutAdvantex.aspx>



APPLICATIONS

M723A is a versatile product that is well suited for very demanding applications including:

- Hand lay-up open mold for boat hulls particularly those involving "wet and carry" processes
- Automated matched metal die closed molds for automotive load floors
- Flat sheet lamination for RV and truck panels



M723A CHOPPED STRAND MAT

FOR DEMANDING APPLICATIONS

AVAILABILITY – Not all products are available in all regions. Additional weights and widths are available upon request

Nominal Mat Weight (g/m ²)	Nominal Mat Weight (oz/ft ²)	Roll Width (cm)	Roll Width (in)
300 – 450 – 600 – 900	1.0 – 1.5 – 2.0 – 3.0	96.5 – 127 – 152.4	38 – 50 – 60

PACKAGING

Nominal Mat Width (cm)	Nominal Mat Width (in)	Roll Diameter (cm)	Roll Diameter (in)	Rolls Per Pallet	Pallet Size (cm)	Pallet Size (in)
96.5 – 127 – 152.4	38 – 50 – 60	28.6	11 ¼	16	114.3 x 114.3	45 x 45

Each roll is wound up on a 101.6mm (4") internal diameter cardboard tube and fully enclosed in Cling-Pak® wrap. 16 rolls are positioned vertically on each pallet, banded with tape and Cling-Pak® wrapped.

LABELLING

Each roll bears a label detailing the product description, product code, nominal weight, roll width, roll number, date of manufacture, and time of manufacture.

STORAGE

Unless otherwise specified, it is recommended to store glass fiber products in a cool, dry area. The best conditions are at a temperature between 10°C and 35°C and a relative humidity between 35% and 85%. The glass fiber products must remain in their original packaging material until the point of usage. If the storage temperature is below 15°C, it is recommended that the product be stored in the workshop, within its original packaging, at least 24 hours prior to use to prevent condensation. The packaging is not waterproof. Be sure to protect the product from the weather and other sources of water. When stored properly, there is no known shelf life to the product, but retesting is advised after three years from the initial production date to insure optimum performance.

Americas

Owens Corning
Composite Materials, LLC.
One Owens Corning Parkway
Toledo
Ohio 43659
1.800.GET.PINK™

Europe

European Owens Corning
Fiberglas Sprl.
166 Chaussée de la Hulpe
B-1170 Brussels
Belgium
+32 2 674 8211

Asia Pacific

Owens Corning - OC Asia Pacific
Shanghai Regional Headquarters
Unit 01, 02,05, 39/F, Pudong Kerry Parkside,
1155 Fang Dian Road, Pudong, Shanghai,
201204, China
+86-21-6101 9666

This information and data contained herein is offered solely as a guide in the selection of reinforcement. The information contained in this publication is based on actual laboratory data and field test experience. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application to determine its suitability before committing to production. It is important for the user to determine the properties of its own commercial compounds when using this or any other reinforcement. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law safety code or insurance regulation. Owens Corning reserves the right to modify this document without prior notice.

© 2014 Owens Corning. All Rights Reserved. Boats picture copyright: Mooncaz / shutterstock.com.

Pub number: 16491-E

M723A Chopped Strand Mat_ww_09_2014_Rev2, September 2014

ChoppedStrandMats@owenscorning.com
www.composites.owenscorning.com